

Contents lists available at ScienceDirect

Catalysis Communications



journal homepage: www.elsevier.com/locate/catcom

Conversion of butanol to propene in flow: A triple dehydration, isomerisation and metathesis cascade

Yiping Shi^{a,*}, Andrew S. Weller^b, A. John Blacker^c, Philip W. Dyer^{a,*}

^a Department of Chemistry, Durham University, South Road, Durham DH1 3LE, UK

^b Department of Chemistry, University of York, York YO10 5DD, UK

^c School of Chemistry, University of Leeds, Woodhouse Lane, Leeds LS2 9JT, UK

| ARTICLE INFO | A B S T R A C T | | |
|---|---|--|--|
| Keywords: Butanol Propene Dehydration Isomerisation Cross-metathesis Flow | A combined three-step flow cascade conversion of <i>n</i> -butanol to propene is demonstrated. Zeolite H-ZSM-5 gives high conversion in the initial <i>n</i> -butanol dehydration step (98%). Subsequent isomerisation of terminal butenes to internal butenes over zeolite H-Fer takes place with good conversion (87%). Finally, cross-metathesis with ethene over a tungsten on acid-washed SiO ₂ /Al ₂ O ₃ catalyst affords propene with good selectivity (65%). Coupling these three steps into a single flow sheet gives an overall yield of 64% propene from <i>n</i> -BuOH. Ethene cross-metathesis catalyst performance was probed using 2-pentene as a model co-substrate giving good conversion (~90%) and moderate selectivity to butenes (67%). | | |

1. Introduction

Industrially, propene is an important building block for the preparation of a wide range of chemicals and is the second most used petrochemical feedstock after ethene [1]. Although the largest market for propene is in the manufacture of polypropene (\sim 70%), the synthesis of propenoic acid, propenonitrile, epoxypropane, (1-methylethyl)benzene, and epoxypropane also consume significant quantities. Traditionally, propene has been produced as a by-product from steam cracking [2] and fluid catalytic cracking [3]. However, the emergence of shale gas resources over the last decade has driven conversion of many cracking units to use ethane as a feed rather than naphtha [4], which has resulted in a very considerable shift of the product slate away from propene to predominantly ethene. Consequently, the supply of propene cannot keep pace with increasing demand (expected to be 135 million tonnes in 2025 [5]), which has made the development of on-purpose propene (OPP) production processes of increasing interest [5]. Today, the three most widely investigated OPP processes are catalytic propane dehydrogenation, the methanol to olefins (MTO) process, and cross-metathesis of ethene with butenes, few of which have reached full commercialisation to date [6].

In parallel, attention is focussing increasingly on more sustainable routes for olefin production, with dehydration of bio-derived ethanol and butanol to ethene and butenes, respectively, being at the forefront of this area [7]. Today there is growing availability of bio-derived butanol, with an estimate of over 247 billion tonnes being produced annually worldwide [8]. Notably, the availability of bio-derived alcohols continues to increase as a result of implementation of processes such as ABE fermentation, which gives a mixture of acetone, butanol and ethanol. However, currently, there are few OPP routes to propene from sustainable feedstocks. For example, a two-stage process has been developed for the production of propene through glycerol hydrogenolysis and subsequent dehydration [9], although a costly iridium-based catalyst is required. The work described in this communication describes a flow triple cascade process that converts *n*-butanol to propene in an integrated fashion. This offers future opportunities for bio-derived propene manufacture.

2. Experimental

Zeolite ferrierite (SAR 20), zeolite beta (SAR 25), zeolite ZSM-5 (SAR 23), zeolite-Y (SAR 80) each as their ammonium forms; ammonium tungsten oxide hydrate; and ammonium molybdate (*para*) tetrahydrate (99%) were purchased from Alfa Aesar. SiO₂ gel, SiO₂/Al₂O₃ support, 1-butene (>99%) and γ -Al₂O₃ were obtained from Sigma Aldrich (Merck). 2-Pentene (*cis*- and *trans*-mixture, >95%) and MgO were sourced from Fluorochem. Ethene (99.9%) was purchased from BOC and was used as received.

* Corresponding authors. E-mail addresses: yiping.shi@durham.ac.uk (Y. Shi), p.w.dyer@durham.ac.uk (P.W. Dyer).

https://doi.org/10.1016/j.catcom.2022.106421

Received 22 November 2021; Received in revised form 24 January 2022; Accepted 27 January 2022 Available online 31 January 2022 1566-7367/© 2022 The Author(s). Published by Elsevier B.V. This is an open access article under the CC BY-NC-ND license

(http://creativecommons.org/licenses/by-nc-nd/4.0/).

Prior to catalysis, the ammonium forms of the zeolites ZSM-5 (SAR 23), ferrierite (SAR 20), Y (SAR 80) and beta (SAR 25) were converted to their corresponding protic forms, H-ZSM-5, H-Fer, H-Y and H-Beta by calcination under static air (NH₄-ZSM-5; heated to 500 °C at 10 °C min⁻¹ and held for 4 h; NH₄-Fer and NH₄-Y: heated to 550 °C at 2 °C min⁻¹ and held for 5 h; NH₄-Beta: heated to 2 °C min⁻¹ to 500 °C and held for 5 h) and then allowed to cool slowly to room temperature before being stored in sealed vials. Before testing, the zeolites (as their acid forms) were pressed into pellets by application of 10 tons pressure for 30 s, and then crushed and sieved to 250–500 µm.

2.1. Catalytic alcohol dehydration

A 1/4" o.d. stainless steel reactor tube was charged with quartz wool (30 mg), pressed, crushed, and sieved zeolite catalyst {acid form} (0.1 g), and finally more quartz wool (30 mg). Testing was done by first heating the catalyst at 150 $^\circ C$ under N_2 for 1 h (N_2 flow rate 30 mL min⁻¹) and then heating the reactor tube to the desired reaction temperature (250 °C) before *n*-butanol was allowed to flow through the catalyst bed using a syringe pump (0.024 mL min⁻¹) after initially passing through a vaporiser unit held at 155 °C. The system is heat traced at 155 °C to ensure substrate and products remain in the gaseous phase. Product analysis for the dehydration step was performed using an on-line GC-FID system (HP5890-II) employing a Stabilwax-DA column (30 m length, 0.25 mm i.d., 0.20 µm film thickness) using the following heating profile: column held at 40 °C for 10 mins prior to and ramping at 30 $^\circ\text{C}$ min $^{-1}$ to 220 $^\circ\text{C}$ where the temperature was held for 3 mins. GC calibration curves for starting materials and products were established using nonane as internal standard. The response factor (R_f) of 1-butene is 0.46 and that of di-n-butyl ether is 0.78. Calculations used to determine butanol conversion by dehydration and for the butene selectivity are given in the SI.

2.2. Olefin isomerisation catalysis

A ¹/4" o.d. stainless steel reactor tube was charged with quartz wool (30 mg), pressed, crushed, and sieved catalyst (0.1 or 0.2 g), and more quartz wool (30 mg). Testing was done by first heating the catalyst at 150 °C under N₂ for 1 h (N₂ flow rate 30 mL min⁻¹), which was then cooled or heated to the desired reaction temperature (20–250 °C) before a flow of 1-butene (6 mL min⁻¹) was passed through the heated catalyst bed. The gaseous products were collected in a gas sampling balloon attached to the outlet tube; the gaseous products were then bubbled slowly *via* a needle through deuterated benzene (0.7 mL) in an NMR tube, which was quickly sealed and thoroughly shaken, and the resulting solution analysed by ¹H NMR spectroscopy (Bruker Advance spectrometer, 400 MHz). Calculations used to determine 1-butene conversion and butene selectivity are given in the SI.

2.3. Catalytic olefin cross-metathesis

2.3.1. Catalyst preparation: incipient wetness impregnation

The catalysts, Mo on SiO₂/Al₂O₃, Mo on SiO₂, Mo on H-Y/ γ -Al₂O₃, were prepared by incipient wetness impregnation using a modification of a literature procedure [10]. The SiO₂/Al₂O₃, SiO₂ and H-Y/ γ -Al₂O₃ supports were dried at 110 °C for 16 h, then calcined at 500 °C for 5 h (2 °C min⁻¹ heating ramp rate) under static air before being allowed to cool slowly to room temperature. The desired amount of ammonium molybdate tetrahydrate was dissolved in a minimum amount of deionised water (based on support pore volumes): 2.6 mL for SiO₂/Al₂O₃; 5.6 mL for SiO₂; 2.0 mL for H-Y/ γ -Al₂O₃. The calcined support was then impregnated by dropwise addition of an aqueous solution of ammonium molybdate tetrahydrate. The resulting materials were then first dried at 110 °C in an oven for 16 h under static air, then subsequently calcined at 400 °C for 2 h (heating rate 1 °C min⁻¹), before being finally allowed to cool slowly to room temperature. All the catalysts were pressed at 10 tons for 30 s before being crushed and sieved to 250–500 $\mu m.$

2.3.2. Catalyst preparation: aqueous impregnation

The materials W on SiO₂/Al₂O₃. Mo on acid washed SiO₂/Al₂O₃, W on acid-washed SiO₂/Al₂O₃, W on SBA-15 were prepared by aqueous impregnation of the support using a modification of a literature procedure [11]. In each case, the desired support was first calcined (500 °C, 15 h, 5 $^{\circ}$ C min⁻¹ heating rate) under static air and allowed to cool slowly to room temperature. Solutions of ammonium molybdate or ammonium tungsten oxide in deionised water were prepared (6.66 g metal per litre, 0.0054 M). The metal-containing catalyst precursor solution (48 mL) was added to a suspension (4 g) of previously-calcined support in deionised water (152 mL) and stirred for 2 h with a magnetic stirrer bar. Water was evaporated using a rotary evaporator at 60 °C, 160 mbar. The resulting solid was dried in an oven under static air at 110 °C overnight, before finally being calcined at 500 °C for 2 h (heating ramp rate 5 °C min⁻¹) and allowed to cool slowly to room temperature. Samples of each of the catalysts were then pressed at 10 tons for 30 s before being crushed and sieved to 250-500 µm.

2.3.3. Catalyst preparation: acid-washed SiO₂/Al₂O₃ support

A round bottomed flask was charged with SiO₂/Al₂O₃ (20 g) and then aqueous HNO₃ (0.05 M, 200 mL) added. The resulting suspension was then heated at 80 °C for 1 h in an oil bath. After cooling, the acid-modified SiO₂/Al₂O₃ was then washed with deionised water (200 mL) using a Buchner filter, before the washed material was dried at 110 °C in an oven under static air overnight. The whole acid wash/water wash process was then repeated a further two times; the resulting material was then used to prepare the metathesis catalysts.

2.3.4. Catalysis

A 1/4" diameter stainless steel reactor tube was charged with quartz wool (30 mg), pressed, crushed, and sieved catalyst (0.2 g) and then more quartz wool (30 mg). Testing was done by first heating the catalyst at 550 °C (heating rate 5 °C min⁻¹) under N₂ (flow rate 8 mL min⁻¹) for 2 h and then allowed to cool to the desired temperature (40-550 °C) at which point the olefin was admitted to the system and allowed to contact the catalyst. When liquid 2-pentene was used as feed, this was added via a syringe pump and vaporiser, while gaseous ethene was introduced directly into the reactor system via a non-return valve with its flow rate controlled by a gas flow meter. The composition of the products produced was analysed on-line using an HP 5890-II GC-FID. The separation of hydrocarbons was performed on an HP-PONA column (50 m length, 0.2 mm i.d., 0.5 µm film thickness), with the temperature held constant at 30 °C for 10 mins. The metathesis activity was measured over one hour on stream for each catalyst. The conversion and selectivity were calculated based on the metathesis products. Calculations used to determine 2-pentene and butenes conversion, and butene and propene selectivity are given in the SI.

3. Results and discussion

A three-step triple cascade system has been developed to convert butanol to propene in flow. The cascade combines *n*-butanol dehydration to butenes (Step A), isomerisation of 1-butene to 2-butenes (Step B), and cross-metathesis of 2-butenes with ethene to afford propene (Step C), as illustrated in Scheme 1. The development of each of these catalytic processes will be considered in turn.

3.1. Dehydration of n-butanol

Industrially, 1-butene is produced principally by two methods. Fractional distillation from a crude C_4 refinery steam, which yields a mixture of 1- and 2-butenes [12] and dimerisation of ethene to yield 1-butene directly [13]. More recently, attention has turned to alternative sustainable routes to butenes, principally focussing on the dehydration



Scheme 1. Conversion of *n*-butanol to propene in a three-step cascade.

of *n*-butanol to the corresponding butenes using zeolite catalysts, which offer high activity at lower reaction temperatures [14]. In this area, H-ZSM-5 has been a particular focus, in part as a result of the computational prediction of its high selectivity towards 1-butene by Reyniers and co-workers [15]. A number of laboratory studies have probed the kinetics of butanol dehydration using H-ZSM-5 [16], however these reactions were carried out at low butanol conversions and did not explore reaction selectivity. In contrast, Urresta [17] and Verberckmoes's group [18] have demonstrated that almost full conversion of *n*-butanol to a mixture of 1-, *cis*- and *trans*-2-butenes can be achieved at 260 °C after optimisation of the Si/Al ratio of the H-ZSM-5 catalyst employed.

Building on this established potential of H-ZSM-5 for n-butanol dehydration, H-ZSM-5 was the catalyst of choice for inclusion in our cascade flow process. Our experimental results confirmed that appropriately activated H-ZSM-5 did indeed perform well [15]. At 250 °C and with 0.024 mL min⁻¹ flow rate, 98% conversion of butanol was achieved, with >99% butene selectivity being maintained for 4 h on stream. Under these conditions a mixture of 1-butene (22%), cis-2-butene (29%) and trans-2-butene (49%) were obtained (Scheme 2). The only side product is di-n-butyl ether (DBE), with the extent of its formation being dependent on both reaction and reactor residence times, with slower space velocities resulting in a lower DBE make. The H-ZSM-5 catalyst maintains conversion of 95% for around 20 h on stream (Fig. 1) with <2% decrease in butene selectivity. However, after 70 h, the conversion drops to \sim 58% (Fig. S4), although DBE remains as the predominant side product (11% after 70 h). Thus, based on this initial screening, H-ZSM-5 was deemed an appropriate n-butanol dehydration catalyst for use in the target cascade system.

3.2. Isomerisation of 1-butene

Following selection of a suitable catalyst and operating parameters for n-butanol dehydration, focus moved to establishing reaction conditions for the necessary butene isomerisation step (Scheme 1, step B). Previously, it has been reported that isomerisation of 1- to 2-butene can be achieved using both homo- and hetero-geneous catalysts [19]. However, this project has focussed only on heterogeneously-catalysed routes. In this context, although 1-butene conversion of over 90% has been achieved using both a well-defined solid-state molecular organometallic (SMOM) catalyst and a MOF system with zeolite-type architecture at room temperature, these catalysts are either air-/moisturesensitive or require high reaction pressures [19,20]. Consequently, this current study has instead explored the potential of a range of stable, cheap and robust commercially-available catalysts targeting high conversion at low reaction pressures. Based on prior literature, both silicon and magnesium oxides have shown good performance for the isomerisation of 1-butene and hence were selected as initial potential candidates in our study [21]. Additionally, computational studies by Marin's

group have also suggested that zeolites are good potential candidates for butene isomerisation [15]. This is in agreement with our own observation that *trans*-2-butene was observed as the major product rather than 1-butene after *n*-butanol dehydration, suggesting that H-ZSM-5 is also active for the isomerisation of 1-butene. Consequently, H-ZSM-5 was also included in our catalyst screen.

Initial catalyst tests were performed using pure 1-butene as a model substrate and a gas flow rate of 6 mL min⁻¹ to mimic the flow rate of the dehydration reaction (0.024 mL min⁻¹ liquid flow rate). To ensure an accurate product composition analysis, reaction products from the flow reactor were collected using a gas sampling balloon, then dissolved in deuterobenzene, and analysed off-line by ¹H NMR spectroscopy.

The performance of appropriately activated silica, magnesium oxide, and zeolites were screened across a range of different reaction temperatures. With silica, only a 9% conversion is obtained at 300 °C, although on raising the reaction temperature to 400 °C the conversion increases to 72% with selectivities to *trans*-2-butene and *cis*-2-butene of 56% and 40%, respectively. Increasing the reaction temperature further to 500 °C does not improve conversion and results in formation of undesirable isobutene (Table 1, Entry 1–4). Using MgO as catalyst even higher reaction temperatures are needed for isomerisation, with only 7% conversion being achieved at 400 °C with 63% and 37% selectivity to *trans* and *cis*-2-butene, respectively. Comparable conversion (~70%) to that obtained with silica at 400 °C is obtained at 500 °C, however, the on-set of isobutene (1%) formation is also observed (Table 1, Entry 5–7). Note, no isomerisation was observed in the absence of a catalyst.

In contrast to silica and magnesium oxides, the zeolites H-ZSM-5, H-Beta and H-Fer all mediate 1-butene isomerisation at significantly lower operating temperatures (Table 1, Entry 8–22). For each of the zeolites, it was found that conversion increases upon raising reaction temperature, reaching a maximum at 150 °C. Operation at higher temperatures (up to 250 °C) results in the formation of small amounts of isobutene (typically \sim 3%). Zeolite H-Fer gives the best results, 87% conversion, with selectivity to cis- and trans-2-butene of 36% and 64%, respectively, as the only products at 150 °C (Table 1, Entry 10). Increasing reactor residence time by doubling the H-Fer catalyst bed length has only a limited impact on conversion (89%), with selectivity essentially unchanged (cis- and trans-2-butene of 35% and 64%, respectively) at 150 °C, which suggests that a thermodynamic equilibrium has been reached under these operating conditions. Indeed, this observed equilibrium composition is in excellent agreement with that previously calculated, namely $\sim 10\%$ of 1-butene in the equilibrium mixture of 1-/ 2-butenes at 150 °C [22]. The results we have obtained here for the isomerisation of butenes using H-Fer as catalyst at atmospheric pressure are comparable to those for the isomerisation of butenes achieved using either a solid-state organometallic catalyst [19] or a MOF-based system at elevated pressure [20]. However, use of H-Fer is preferable since it is both easy to handle (air-/moisture stable) and operates at atmospheric



Scheme 2. Conversion of *n*-butanol using H-ZSM-5 as catalyst. Conditions: H-ZSM-5 (Si:Al 23, 0.1 g), catalyst pre-activated at 150 °C under N_2 flow for 1 h. Dehydration reaction carried out at 250 °C with 0.024 mL min⁻¹ flow rate of n-butanol at atmospheric pressure; vaporiser and connections heat traced to 155 °C.



Dehydration of butanol with H-ZSM-5

Fig. 1. Conversion of *n*-butanol to butene with H-ZSM-5 at 250 °C, 0.024 mL min⁻¹ flow rate for 24 h on stream.

 Table 1

 Screening results for 1-butene isomerisation with catalysts at different reaction temperatures.

| Entry | Catalyst | T (°C) | Conv (%) | trans-2- butene (%) | cis-2- butene (%) | Isobutene (%) |
|-------|------------------|-------------------------|-------------|------------------------|-------------------------|------------------|
| 1 | SiO_2 | 20- 250 ^a | 0 | 0 | 0 | 0 |
| 2 | SiO ₂ | 300 | 9 | 56 | 44 | 0 |
| 3 | SiO ₂ | 400 | 72 | 56 | 40 | 4 |
| 4 | SiO ₂ | 500 | 71 | 51 | 38 | 11 |
| 5 | MgO | 20- 300 ^b | 0 | 0 | 0 | 0 |
| 6 | MgO | 400 | 7 | 63 | 37 | 0 |
| 7 | MgO | 500 | 70 | 57 | 43 | 1 |
| 8 | H-Fer | 20- 50 ^c | 0 | 0 | 0 | 0 |
| 9 | H-Fer | 100 | 37 | 54 | 46 | 0 |
| 10 | H-Fer | 150 | 87 | 64 | 36 | 0 |
| 11 | H-Fer | 200 | 85 | 62 | 38 | 0 |
| 12 | H-Fer | 250 | 81 | 57 | 39 | 4 |
| 13 | H-ZSM- 5 | 20- 50 ^c | 0 | 0 | 0 | 0 |
| 14 | H-ZSM- 5 | 100 | 25 | 56 | 44 | 0 |
| 15 | H-ZSM- 5 | 150 | 84 | 63 | 37 | 0 |
| 16 | H-ZSM- 5 | 200 | 85 | 62 | 38 | 0 |
| 17 | H-ZSM- 5 | 250 | 81 | 59 | 38 | 3 |
| 18 | H-beta | 20- 50 ^c | 0 | 0 | 0 | 0 |
| 19 | H-beta | 100 | 20 | 50 | 50 | 0 |
| 20 | H-beta | 150 | 79 | 61 | 39 | 0 |
| 21 | H-beta | 200 | 83 | 62 | 37 | 1 |
| 22 | H-beta | 250 | 80 | 59 | 37 | 4 |

Conditions: catalyst (0.1 g) pressed and sieved to $250-500 \mu$ m, flow of 1-butene (6 mL min⁻¹), results analysed by ¹H NMR spectroscopy.

 $^{\rm a}$ Individual reactions carried out at 20, 50, 100, 150, 200 and 250 $^\circ \rm C,$ each gave no conversion.

 $^{\rm b}$ Individual reactions carried out at 20, 50, 100, 150, 200, 250 and 300 $^\circ C,$ each gave no conversion.

^c Individual reactions carried out at 20 and 50 °C, each gave no conversion.

pressure.

3.3. Cross-metathesis of cis-/trans-2-pentene with ethene

After the successful conversion of terminal butene to internal butenes, the next step in establishing a cascade for *n*-butanol to propene production was to establish a method for the conversion of the internal butenes to the target C3 alkene via cross-metathesis with ethene (Scheme 1, step C). In the literature, silica- and/or alumina-supported molybdenum and tungsten catalysts have been reported to demonstrate appropriate olefin cross-metathesis performance with similar α -olefins [23]. However, the cross-metathesis performance of these classes of catalyst demonstrate significant substrate-specific reaction conditions. For example, propene/ethene cross-metathesis can be achieved at 40 °C with MoO₃ on SiO₂/Al₂O₃ [24], while for pentene/ethene, over 500 °C is necessary to be obtain a reasonable conversion (~50%) with either Mo or W supported on SBA-15 (a well-defined mesoporous silica) [25]. Moreover, it is well established that the performance of olefin metathesis catalysts under industrially-relevant conditions is challenging as a result of low reaction rates and mediocre activities, which together necessitate forcing operating conditions. Consequently, for the current study, it was necessary to establish optimal reaction conditions for the specific substrates of interest, namely butenes.

Initially, determination of reaction conditions for the required ethene cross-metathesis transformation were explored using cis-/trans-2pentene as substrate since this is an easily manipulable model liquid substrate, compared to gaseous butenes. Thus, cross-metathesis performance of a series of molybdenum- and tungsten-based catalysts supported on silica, silica-alumina and H-Y/alumina and SBA-15 supports were probed for conversion of ethene and cis-/trans-2-pentene (in a ratio 1:1, respectively) to butenes, measured over a period of one hour on stream (Table 2). Consistent with data from the literature for related heterogeneous metathesis catalysts [25], no conversion of cis-/trans-2pentene was obtained below 250 °C (Table 2). With the Mo on SiO₂/ Al₂O₃ catalyst, the selectivity to butene was low even at 500 °C (Table 2, Entries 2 and 3), with the 2-pentenes principally being isomerised to 1pentene and the three isopentenes. Changing the SiO₂/Al₂O₃ support to H-Y/Al₂O₃ made little difference (Table 2, Entry 4), while with silica as the support, the selectivity of butene increased to around 10% (Table 2, Entry 5). Encouragingly, however, with supported tungsten catalysts (W on SiO₂/Al₂O₃), 70% conversion of 2-pentenes was obtained with 49% selectivity to butenes, with the other products comprising 1-pentene, isopentenes and higher olefins (Table 2, Entry 6). Since it is known

Table 2

Screening of catalysts for 2-pentene/ethene cross-metathesis.



| Entry | Catalyst | Temperature (°C) | Conversion (%) | Butenes selectivity (%) |
|-------|--|------------------|----------------|-------------------------|
| 1 | Mo on SiO ₂ /Al ₂ O ₃ | 40 | 0 | 0 |
| 2 | Mo on SiO ₂ /Al ₂ O ₃ | 250 | 65 | 0 |
| 3 | Mo on SiO ₂ /Al ₂ O ₃ | 500 | 60 | 2 |
| 4 | Mo on H-Y/Al ₂ O ₃ | 500 | 63 | 3 |
| 5 | Mo on SiO ₂ gel | 500 | 64 | 11 |
| 6 | W on SiO ₂ /Al ₂ O ₃ | 500 | 70 | 49 |
| 7 | Mo on acid-washed SiO ₂ /Al ₂ O ₃ | 500 | 60 | 14 |
| 8 | W on acid-washed SiO ₂ /Al ₂ O ₃ | 500 | 90 | 67 |
| 9 | W on acid-washed SiO ₂ /Al ₂ O ₃ | 300 | 62 | 1 |
| 10 | W on SBA-15 | 500 | 62 | 10 |
| 11 | W on SBA-15 | 550 | 70 | 32 |

Reagents and conditions: catalyst (0.2 g) pressed, crushed, and sieved to 250–500 µm, flow of ethene (5 mL min⁻¹), flow of liquid 2-pentene (0.024 mL min⁻¹), results analysed by on-line GC-FID.

that acid washing of γ -Al₂O₃ leads to partial dissolution of alumina and results in a slight increase in the support's acidity and hence more active sites [26], a similar process was tested with the SiO₂/Al₂O₃ support and any impact on subsequent cross-metathesis activity probed. Consequently, a series of new tungsten and molybdenum catalysts was prepared using nitric acid-washed SiO₂/Al₂O₃. The resulting molybdenum catalysts demonstrate a slight increase in butenes formation from 2% to 14% (Table 2, Entry 7 vs Entry 3) compared with that achieved employing the corresponding unmodified support. Significantly, the related tungsten/acid-washed SiO₂/Al₂O₃ supported catalysts show significantly better cross-metathesis activity, with 90% pentene conversion and 67% butene selectivity being obtained (Table 2, Entry 8, c.f. Entry 6, Fig. 2). As observed for the catalysts with unmodified supports, operation at 500 °C is also essential for the systems employing acidwashed SiO₂/Al₂O₃, with, for example, only 1% butene selectivity and 62% conversion to mainly isomerised products being obtained at 300 °C (Table 2, Entry 9). This performance enhancement achieved with the acid-washed supports is in good agreement with the notion that as a result of a Brønsted/Lewis acid synergy, dealuminated zeolite frameworks demonstrate significantly enhanced acidity, which is what is achieved here through acid washing [27]. Thus, we propose that for the W on acid-washed SiO₂/Al₂O₃ catalyst, the increased availability of Brønsted acid sites proximate to the assumed metathesis-active tungsten sites, namely the tungstacyclobutane intermediate (Chauvin mechanism), promotes their reactivity and hence cross-metathesis activity, as evidenced recently with zeolitic framework supports [28].

Notably, this new, cheap, and readily accessible tungsten/acidwashed SiO₂/Al₂O₃-supported system shows better metathesis performance than the best previously reported heterogeneous cross-metathesis catalysts for ethene/pentenes. Under comparable operating conditions, tungsten/SBA-15 (Table 2, Entry 8 vs 10) performed less well (70% conversion, 32% butene selectivity) and required a higher reaction temperature of 550 °C (Table 2, Entry 11 vs Entry 8) [25]. Thus, the tungsten on acid-washed SiO2/Al2O3 catalyst was chosen for incorporation into the combined cascade system for ethene/butenes crossmetathesis where higher selectivity may be expected than with ethene/2-pentene since cracking rates increase dramatically with the carbon number of the olefinic substrate [29].

3.4. Cascade catalysis system

With realistic catalysts and operating systems in hand, the next target was to couple the three reaction steps A-C, namely dehydration, isomerisation, and cross-metathesis (Scheme 1), into a single triple cascade flow sheet, Fig. 3. To the best of our knowledge, only one previous report in the open literature has described this type of approach for the conversion of butanol to propene. Sieber and co-workers disclosed the use of a biocatalytic pathway employing Cytochrome P450 fatty acid decarboxylase OleT_{JE} to convert sequentially butanol to butanal, butanal to butanoic acid and finally butanoic acid to propene in batch reactors [30]. In contrast, our method employing easily prepared heterogeneous catalysts in a flow system has the benefit of ease of catalyst/product



Cross-metathesis of 2-pentene/ ethene with W on acid

Fig. 2. Conversion of 2-pentene to butenes with W on acid-washed SiO₂/Al₂O₃ 500 °C, 0.024 mL min⁻¹ flow rate for 2-pentene (Entry 8, Table 2).



Fig. 3. Overall reaction scheme and reactor arrangement used to convert n-BuOH to propene in a triple cascade.

separation as well as continuous operation.

To achieve a cascade process, a preliminary study employing a combination of three separately-heated reactor systems in series has been explored (Fig. 3). n-Butanol was introduced into the system by a syringe pump with a flow rate of 0.024 mL min⁻¹ and subsequently gasified in the vaporiser (155 °C) before passing sequentially into reactors 1 and 2, with the resultant product stream then being mixed with ethene (flow rate of 6 mL min⁻¹) prior to entry into reactor 3 (estimated ratio of butenes: ethene \sim 1:1). The final product gas stream was analysed on line using a GC-FID. An overall *n*-butanol to propene yield of 64% was obtained using W on acid-washed SiO₂/Al₂O₃. This level of unoptimized *n*-BuOH to propene conversion in a single flow sheet is particularly noteworthy since the best performing heterogeneous catalyst for just the step involving cross-metathesis of pure ethene/trans-2butene, namely zeolite USY-supported WOx, achieves a propene yield of 79% with 80% selectivity [31]. Indeed, other established crossmetathesis catalysts for the conversion of butenes to propene, such as W-H/Al₂O₃ [32], and mixed WO₃/SiO₂/MgO [33], both demonstrate comparable performance to that of the best WO_x-containing commercial catalyst [33].

We suggest that the moderate overall conversion and selectivity achieved herein by linking catalytic systems comprising H-ZSM-5, H-Fer, and W on acid-washed SiO₂/Al₂O₃ in series is a result of several factors. The water produced from the initial *n*-butanol dehydration reaction is likely to interact detrimentally with the Lewis acidic tungsten centre of the cross-metathesis catalyst. Additionally, both the dehydration and isomerisation steps result in a mixture of isomeric butenes, not least a mixture of *cis-/trans*-2-butene, which is problematic since the rate of cross-metathesis of *cis*-2-butene is considerably slower than that of *trans*-2-butene [34]. It is also well established that water can cause irreversible zeolite deactivation due to dealumination [35]. Thus, it is likely that an improved process will need to incorporate a water removal step.

4. Conclusion

A catalyst screening study has shown that the appropriately treated

zeolites H-ZSM-5 and H-Fer show good activities, conversions, and lifetimes for *n*-butanol dehydration and butene isomerisation, respectively. Similarly, the work presented herein shows that a novel, cheap, and readily prepared, but unoptimised tungsten on acid-washed SiO_2/Al_2O_3 catalyst gives encouraging butene/ethene cross-metathesis performance. Building on information derived from these three independent screening/evaluation studies, we have demonstrated the possibility of using a simple three-reactor cascade process for the conversion of *n*butanol to propene in flow. Although only moderate conversions and selectivities have been achieved, it is anticipated that further optimisation, principally incorporating water removal stages, will lead to a viable catalytic methodology for the commercial production of the key feedstock propene from a bio-derived *n*-butanol feed and that developing systems realistic catalyst lifetimes is likely to be challenging.

Author contributions

Y.S., A.J.B., A.S.W., and P.W.D. contributed to the design of the study; Y.S. conducted experiments and data analysis. Y.S. wrote the manuscript and supporting information, with all authors commenting on and amending both documents. All authors discussed and contributed to the work.

Declaration of Competing Interest

There are no conflicts of interest to declare.

Acknowledgement

We thank the EPSRC, UKRI, and the UK Catalysis Hub for funding (EP/R026815/1).

Appendix A. Supplementary data

Supplementary data to this article can be found online at https://doi.org/10.1016/j.catcom.2022.106421.

Y. Shi et al.

References

- W.F. Condrad, H. Wittcoff, R.E. Varnerin, Ethylene: the organic chemical industry's most important building block, J. Chem. Educ. 56 (1979) 385–387, https://doi. org/10.2307/333272.
- [2] A. Akah, M. Al-Ghrami, M. Saeed, M.A.B. Siddiqui, Reactivity of naphtha fractions for light olefins production, Int. J. Ind. Chem. 8 (2017) 221–233, https://doi.org/ 10.1007/s40090-016-0106-8.
- [3] Z. Gholami, F. Gholami, Z. Tišler, M. Tomas, M. Vakili, A review on production of light olefins via fluid catalytic cracking, Energies 14 (2021) 1089–1125, https:// doi.org/10.3390/en14041089.
- [4] I. Amghizar, L.A. Vandewalle, K.M. Van Geem, G.B. Marin, New trends in olefin production, Engineering 3 (2017) 171–178, https://doi.org/10.1016/J. ENG.2017.02.006.
- [5] T.K. Phung, T.L.M. Pham, K.B. Vu, G. Busca, (Bio)propylene production processes: a critical review, J. Environ. Chem. Eng. 9 (2021), 105673, https://doi.org/ 10.1016/j.jece.2021.105673.
- [6] L. Rochlitz, K. Searles, J. Alfke, D. Zemlyanov, O.V. Safonova, C. Copéret, Silicasupported, narrowly distributed, subnanometric Pt-Zn particles from single sites with high propane dehydrogenation performance, Chem. Sci. 11 (2020) 1549–1555, https://doi.org/10.1039/c9sc05599a.
- [7] V. Zacharopoulou, A.A. Lemonidou, Olefins from biomass intermediates: a review, Catalysts 8 (2018) 2, https://doi.org/10.3390/catal8010002.
- [8] D. Kushwaha, N. Srivastava, I. Mishra, S.N. Upadhyay, P.K. Mishra, Recent trends in biobutanol production, Rev. Chem. Eng. 35 (2019) 475–504, https://doi.org/ 10.1515/revce-2017-0041.
- [9] L. Yu, J. Yuan, Q. Zhang, Y.M. Liu, H.Y. He, K.N. Fan, Y. Cao, Propylene from renewable resources: catalytic conversion of glycerol into propylene, ChemSusChem 7 (2014) 743–747, https://doi.org/10.1002/cssc.201301041.
- [10] V.A. Kondratenko, T. Hahn, U. Bentrup, D. Linke, E.V. Kondratenko, Metathesis of ethylene and 2-butene over MoO_x/Al₂O₃-SiO₂: effect of MoO_x structure on formation of active sites and propene selectivity, J. Catal. 360 (2018) 135–144, https://doi.org/10.1016/j.jcat.2018.02.002.
- [11] D.P. Debecker, M. Stoyanova, U. Rodemerck, E.M. Gaigneaux, Preparation of MoO₃/SiO₂-Al₂O₃ metathesis catalysts via wet impregnation with different Mo precursors, J. Mol. Catal. A Chem. 340 (2011) 65–76, https://doi.org/10.1016/j. molcata.2011.03.011.
- [12] B.S. Greensfelder, H.H. Voge, Catalytic cracking of pure hydrocarbons, Ind. Eng. Chem. Res. 37 (1945) 514–520, https://doi.org/10.1016/S0360-0564(08)60107-8.
- [13] A.M. Al-Jaralleh, J.A. Anabtawi, M.A.B. Siddiqui, A.M. Aitani, A.W. Al-Sa'doun, Ethylene dimerization and oligomerization to butene-1 and linear α-olefins: a review of catalytic systems and processes, J. Catal. Today 14 (1992) 1–121, https://doi.org/10.1016/0920-5861(92)80128-A.
- [14] M.A. Makarova, E.A. Paukshtis, J.M. Thomas, C. Williams, K.I. Zamaraev, Dehydration of *n*-butanol on zeolite H-ZSM-5 and amorphous aluminosilicate: detailed mechanistic study and the effect of pore confinement, J. Catal. 149 (1994) 36–51, https://doi.org/10.1006/jcat.1994.1270.
- [15] M. John, K. Alexopoulos, M.F. Reyniers, G.B. Marin, Effect of zeolite confinement on the conversion of 1-butanol to butene isomers: mechanistic insights from DFT based microkinetic modelling, Catal. Sci. Technol. 7 (2017) 2978–2997, https:// doi.org/10.1039/c7cy00536a.
- [16] D. Gunst, M. Sabbe, M.F. Reyniers, A. Verberckmoes, Study of *n*-butanol conversion to butenes: effect of Si/Al ratio on activity, selectivity and kinetics, Appl. Catal. A Gen. 582 (2019) 28–31, https://doi.org/10.1016/j.apcata.2019.05.035.
- [17] J. Urresta, Deshidratacion de los alcoholes presentes en el aceite fusel y su conversión en alquenos empleando una zeolita tipo HZSM-5, Ing. Y Compet. 16 (2014) 79–90, https://doi.org/10.25100/iyc.v16i2.3685.
- [18] D. Gunst, M. Sabbe, M.F. Reyniers, A. Verberckmoes, Study of *n*-butanol conversion to butenes: effect of Si/Al ratio on activity, selectivity and kinetics, Appl. Catal. A Gen. 582 (2019), 117101, https://doi.org/10.1016/j.apcata.2019.05.035.

- [19] F.M. Chadwick, A.I. McKay, A.J. Martinez-Martinez, N.H. Rees, T. Krämer, S. A. Macgregor, A.S. Weller, Solid-state molecular organometallic chemistry. Singlecrystal to single-crystal reactivity and catalysis with light hydrocarbon substrates, Chem. Sci. 8 (2017) 6014–6029, https://doi.org/10.1039/c7sc01491k.
- [20] D. Sheng, Y. Zhang, Q. Song, G. Xu, D. Peng, H. Hou, R. Xie, D. Shan, P. Liu, Isomerization of 1-butene to 2-butene catalyzed by metal-organic frameworks, Organometallics 39 (2020) 51–57, https://doi.org/10.1021/acs. organomet.9b00559.
- [21] K. Ountaksinkul, S. Wannakao, P. Praserthdam, S. Assabumrungrat, Intrinsic kinetic study of 1-butene isomerization over magnesium oxide catalyst: via a Berty stationary catalyst basket reactor, RSC Adv. 10 (2020) 36667–36677, https://doi. org/10.1039/d0ra05453d.
- [22] A.V. Lavrenov, N.M. Ostrovskii, Y.K. Demanov, Thermodynamics of isomerization of butylenes: equilibrium compositions, Pet. Chem. 41 (2001) 126–130. https:// www.cheric.org/research/tech/periodicals/view.php?seq=1032201.
- [23] H. Zhang, Y. Li, S. Shao, H. Wu, P. Wu, Grubbs-type catalysts immobilized on SBA-15: a novel heterogeneous catalyst for olefin metathesis, J. Mol. Catal. A Chem. 372 (2013) 35, https://doi.org/10.1016/j.molcata.2013.01.034.
- [24] D.P. Debecker, M. Stoyanova, F. Colbeau-Justin, U. Rodemerck, C. Boissiāre, E. M. Gaigneaux, C. Sanchez, One-pot aerosol route to MoO₃-SiO₂-Al₂O₃ catalysts with ordered super microporosity and high olefin metathesis activity, Angew. Chem. Int. Ed. 51 (2012) 2129–2131, https://doi.org/10.1002/anie.201106277.
- [25] M.A. Ibrahim, M.N. Akhtar, J. Čejka, E. Montanari, H. Balcar, M. Kubů, S.S. Al-Khattaf, Metathesis of 2-pentene over Mo and W supported mesoporous molecular sieves MCM-41 and SBA-15, J. Ind. Eng. Chem. 53 (2017) 119–126, https://doi. org/10.1016/j.jiec.2017.04.012.
- [26] S.B. Sasongko, D.D. Anggoro, L. Buchori, R. Febrianto, E.A.B. Siagian, The effect of dealumination process on zeolite Y acidity and morphology, AIP Conf. Proc. 2197 (2020), 050001, https://doi.org/10.1063/1.5140913.
- [27] S. Li, A. Zheng, Y. Su, H. Zhang, L. Chen, J. Yang, C. Ye, F. Deng, Brønsted/Lewis acid synergy in dealuminated HY zeolite: a combined solid-state NMR and theoretical calculation study, J. Am. Chem. Soc. 129 (2007) 11161–11171, https:// doi.org/10.1021/ja072767y.
- [28] P. Zhao, L. Ye, G. Li, C. Huang, S. Wu, P.L. Ho, H. Wang, T. Yoskamtorn, D. Sheptyakov, G. Cibin, A.I. Kirkland, C.C. Tang, A. Zheng, W. Xue, D. Mei, K. Suriye, S.C. Edman Tsang, Rational design of synergistic active sites for catalytic ethene/2butene cross-metathesis in a rhenium-doped Y zeolite catalyst, ACS Catal. 11 (2021) 3530–3540, https://doi.org/10.1021/acscatal.100524.
- [29] J.S. Buchanan, J.G. Santiesteban, W.O. Haag, Mechanistic considerations in acidcatalyzed cracking of olefins, J. Catal. 158 (1996) 279–287, https://doi.org/ 10.1006/jcat.1996.0027.
- [30] D. Bauer, I. Zachos, V. Sieber, Production of propene from n-butanol: a three-step cascade utilizing the cytochrome P450 fatty acid decarboxylase OleTJE, ChemBioChem 21 (2020) 3273–3281, https://doi.org/10.1002/cbic.202000378.
- [31] P. Zhao, L. Ye, Z. Sun, B.T.W. Lo, H. Woodcock, C. Huang, C. Tang, A.I. Kirkland, D. Mei, S.C. Edman Tsang, Entrapped single tungstate site in zeolite for cooperative catalysis of olefin metathesis with Brønsted acid site, J. Am. Chem. Soc. 140 (2018) 6661–6667, https://doi.org/10.1021/jacs.8b03012.
- [32] E. Mazoyer, K.C. Szeto, N. Merle, S. Norsic, O. Boyron, J.M. Basset, M. Taoufik, C. P. Nicholas, Study of ethylene/2-butene cross-metathesis over W-H/Al₂O₃ for propylene production: effect of the temperature and reactant ratios on the productivity and deactivation, J. Catal. 301 (2013) 1–7, https://doi.org/10.1016/j. jcat.2013.01.016.
- [33] J.C. Mol, Industrial applications of olefin metathesis, J. Mol. Catal. A Chem. 213 (2004) 39–45, https://doi.org/10.1016/j.molcata.2003.10.049.
- [34] J. Engelhardt, I. Zsinka, Stereochemistry in cross-metathesis of 1-butene with cisand trans-2-butene over MoO₃/Al₂O₃ and Re₂O₇/Al₂O₃ catalysts, J. Mol. Catal. 28 (1985) 169–182, https://doi.org/10.1016/0304-5102(85)87026-7.
- [35] K. Stanciakova, B.M. Weckhuysen, Water-active site interactions in zeolites and their relevance in catalysis, Trends Chem. 3 (2021) 456–468, https://doi.org/ 10.1016/j.trechm.2021.03.004.