Muon spectroscopy investigation of anomalous dynamic magnetism in NiI₂

T. L. Breeze, ¹B. M. Huddart, ^{1,2}A. Hernández-Melián, ¹N. P. Bentley, ¹D. A. Mayoh, ³G. D. A. Wood, ^{3,4}

G. Balakrishnan[®],³ J. Wilkinson[®],⁴ F. L. Pratt[®],⁴ T. J. Hicken[®],⁵ S. J. Clark[®],¹ and T. Lancaster[®]

¹Department of Physics, Center for Materials Physics, Durham University, Durham DH1 3LE, United Kingdom

²*Clarendon Laboratory, University of Oxford, Department of Physics, Oxford OX1 3PU, United Kingdom*

³Department of Physics, University of Warwick, Coventry CV4 7AL, United Kingdom

⁴ISIS Facility, STFC-Rutherford Appleton Laboratory, Harwell Science and Innovation Campus, Didcot OX11 0QX, United Kingdom ⁵PSI Center for Neutron and Muon Sciences CNM, 5232 Villigen, Switzerland

(Received 5 July 2024; revised 31 January 2025; accepted 24 February 2025; published 17 March 2025)

We present the results of muon-spin relaxation (μ^+ SR) measurements of the van der Waals magnet NiI₂, which probe magnetic phase transitions at $T_{N1} = 73$ K and $T_{N2} = 62$ K. Supporting density functional theory (DFT) calculations allow the determination of a single muon stopping site whose magnetic environment is consistent with the proposed ground-state magnetic structure. μ^+ SR measurements of the dynamics reveal behavior consistent with spin-wave excitations below T_{N2} . In the region $T_{N2} < T < T_{N1}$ the character of the dynamics changes qualitatively, resulting in an unusual region of temperature-independent fluctuations.

DOI: 10.1103/PhysRevB.111.104420

I. INTRODUCTION

Magnetic van der Waals materials are two-dimensional (2D) crystals containing magnetic elements, expected to exhibit intrinsic low-dimensional magnetic properties. These cleavable materials provide a platform for exploring magnetism in the 2D limit, where a range of emergent phenomena are expected [1,2]. Aims in this field include the stabilization of topological spin textures, such as vortices, skyrmions, or merons [3], or the realization of novel topological magnetic states of matter, featuring topological order or band structures [4,5]. NiI₂ is a member of the transition-metal dihalides, a family of materials previously noted for multiferroic behavior [6], with NiI₂ itself displaying ferroelectricity and antiferromagnetic order in its ground state [7]. Recently, it has been proposed that it hosts a novel form of skyrmion phase in the 2D limit [8–10]. Muon spectroscopy is a sensitive probe of low-dimensional magnetism and the dynamics resulting from topological excitations [11-15]. Here we use the technique to investigate the magnetic transitions in NiI2 and the lowtemperature magnetic dynamics. The magnetic ground state is shown to host conventional spin wave dynamic excitations, despite its complicated helical magnetic structure. The regime close to the magnetic ordering temperature is found to have a distinct and unconventional temperature-independent dynamic signature.

NiI₂ is a centrosymmetric magnetic semiconductor long known for its helimagnetism [7,16–20]. The material crystallizes in the rhombohedral CdCl₂-type structure ($R\bar{3}m$) with a magnetic Ni²⁺ ion (S = 1) carrying an ordered moment of $1.6\mu_{\rm B}$ [6,7]. A single layer of NiI₂ is characterized by a triangular net of magnetic cations and competing ferromagnetic and antiferromagnetic interactions, resulting in strong magnetic frustration. The static bulk magnetic susceptibility of single crystals show features at $T_{N1} = 76$ K and $T_{N2} = 58$ K that suggest two successive antiferromagnetic phase transitions in zero applied magnetic field [7]. Evidence of these transitions is also seen in features in the specific heat capacity [18]. The higher-temperature transition at T_{N1} takes the system from a paramagnetic high-temperature phase, to an antiferromagnetic phase on cooling in which, for $T_{N2} < T < T_{N1}$, the magnetic order comprises ferromagnetic planes coupled antiferromagnetically along the c axis [7]. At the lowertemperature transition at T_{N2} the symmetry of the crystal structure changes from trigonal to monoclinic with decreasing temperature, owing to a slight shift in the Ni layers along the *a* direction giving an overall tilt. This structural distortion causes the spin texture to transform into a screw-helimagnetic ground state with propagation vector $\mathbf{q} = (0.138, 0, 0.1457)$ in the lattice basis [21]. Here the **q** vector is slanted from the triangular-lattice basal plane and, correspondingly, the spinspiral plane is also canted from the plane that includes the [001] axis (Fig. 1). In the resulting helimagnetic screw-spin ordered ground state, NiI₂ shows spin-driven ferroelectricity, while the intermediate magnetic state between T_{N1} and T_{N2} is paraelectric [7].

Magnetically, the transition reported at $T_{N1} = 76$ K has not been investigated in detail, with several earlier studies focusing on the low-temperature multiferroic properties [10,22– 24]. The prediction of skyrmionic spin excitations close to the ordering temperature in monolayers of NiI₂ motivates this investigation of the ordering behavior of the bulk material and its dynamics at a local level. We present the results of μ^+ SR experiments on high-quality single crystal and polycrystalline samples of NiI₂ along with discussion of the results paired with an analysis of candidate muon stopping sites and the

Published by the American Physical Society under the terms of the Creative Commons Attribution 4.0 International license. Further distribution of this work must maintain attribution to the author(s) and the published article's title, journal citation, and DOI.



FIG. 1. (a) NiI₂ structure and magnetic ground state showing Ni²⁺ ions (green) and I⁻ ions (purple). The structure comprises stacked trigonal layers of magnetic Ni²⁺ ions. Arrows indicate spins. (b) Low-energy candidate muon stopping site (blue) with (c) the associated field distribution, p(B), (arbitrary units) with a mean field of 0.87 T indicated by the dashed line.

dynamics in the ordered regime. Our results, while being consistent with the reported magnetic ground state of the system, also suggest that the temperature regime $T_{N2} < T < T_{N1}$ is characterized by an unusual spectrum of fluctuations in which the observed muon relaxation is temperature independent, whereas at temperatures below T_{N2} the material exhibits more conventional dynamic magnetism.

II. EXPERIMENTAL METHODS

We grew single crystals of NiI₂ by the Bridgman method [25]. Stoichiometric quantities of Ni and I were inserted into a quartz tube which was then sealed under vacuum. The tube was inserted into a vertical Bridgman furnace and slowly heated to 750 °C. The tube was then slowly cooled at 1 °C/hr to 600 °C. Once at 600 °C the tube was then rapidly cooled to room temperature and then removed from the furnace. We have characterized our samples by carrying out field-cooled magnetic susceptibility measurements, which are also in agreement with previous results [7].

In a μ^+ SR experiment, spin-polarized muons are implanted in a sample where they interact with the local magnetic field at the muon site. After, on average, 2.2 µs, the muons decay into a positron and two neutrinos. By detecting the positrons, which are preferentially emitted in the direction of the muon spin at the time of decay, we can track the polarization of the muon-spin ensemble [26]. In a zero-field (ZF) μ^+ SR experiment, the local magnetic field at the muon sites arises largely due to the configuration of the spins in the system. When the muon-spin has a component perpendicular to the local field B, precession occurs with angular frequency $\omega = \gamma_{\mu} B$, where $\gamma_{\mu} = 2\pi \times 135.5 \text{ MHz T}^{-1}$ is the gyromagnetic ratio of the muon. When the muon-spin aligns with the local field, only dynamic fluctuations can depolarize the muon-spin ensemble. The quantity of interest in the experiment is the asymmetry A(t), calculated from counts measured in the detectors forwards and backwards of the initial muon-spin polarization direction N_{F,B}, corrected using a parameter α reflecting detector efficiency, via $A(t) = (N_{\rm F} - 1)^2$ $\alpha N_{\rm B})/(N_{\rm F} + \alpha N_{\rm B})$. The asymmetry is directly proportional to the polarization of the muon ensemble. Spectra were fitted using the WiMDA fitting program [27].

III. RESULTS AND DISCUSSION

We made zero-field (ZF) μ^+ SR measurements at temperatures from 1.7 K to 80 K using the GPS spectrometer at S μ S [28], with points concentrated close to the two transitions. Measurements were made on a single crystal sample comprising of a disk of NiI₂ with the *c* axis parallel to the initial muon-spin polarization. Below T_{N1} , oscillations are observed in the muon asymmetry, corresponding to long-range magnetic order (LRO) occurring throughout the bulk of the material. We find that a good fit is achieved with only one oscillatory frequency with no phase offset, indicating a dominant contribution to the asymmetry signal from a single muon stopping site. We fit the measured asymmetry to a model of the form

$$A(t) = A_1 e^{-\lambda_1 t} \cos(2\pi \nu_1 t) + A_2 e^{-\lambda_2 t} + A_3, \qquad (1)$$

where the first term corresponds to a relaxing precession of the muon spin components perpendicular to the local magnetic field. Terms two and three are relaxing and constant background components, respectively, with the former due to those muon-spin components initially parallel to the internal magnetic field. For our single crystal measurement we find that the ratio $A_1 : A_2$ is roughly 3:1. Over the range of temperatures up to 72 K, the data exhibit very fast damping of the oscillatory term (with the oscillations only visible for roughly the first 0.1 µs). We find the oscillating component relaxes much faster than the purely exponential component and the short time window at SµS makes changes in λ_2 difficult to fit. In fitting the data, the relaxing amplitudes A_1 and A_2 are held constant, as is λ_2 . We do observe that A_1 appears to increase slightly above T_{N2} , but consistent fitting of this parameter is made difficult by the fact that the asymmetry data begins at around $t = 0.003 \,\mu s$ and the oscillations are fast enough that a significant portion of an oscillation has occurred already at this stage so we choose to hold it constant in our fitting. Example spectra showing this change are included in the Supplemental Material [29]. Above $T \approx 72$ K the oscillations are no longer visible. Figure 2 shows plots of the fitted



FIG. 2. Temperature evolution of ZF μ^+ SR fitting parameters. (a) The precession frequency ν_1 with equivalent local field *B* shown on the right-hand axis and (b) the associated relaxation rate λ_1 . (c) Inset: example μ^+ SR spectrum at 3 K with fit in red, plotted as percentage asymmetry. The frequency ν_1 in (a) drops to zero at T_{N1} , indicating the absence of long-range order above this temperature. The transition at T_{N2} is seen in a discontinuous change in the gradient of ν . Red lines are fits generated using Eqs. (1) and (2). In (b) the relaxation rate λ_1 is fixed at $120 \,\mu \text{s}^{-1}$ in the fitting routine below 50 K.

parameters, including frequencies v_1 against temperature. The data above 62 K are fitted to a model

$$\nu_1(T) = \nu_0 [1 - (T/T_N)^{\delta}]^{\beta}, \qquad (2)$$

where T_N is a critical temperature and v_1 is an effective order parameter for the magnetic phase transition. We find $T_{\rm N1} = 72.5(1) \,\text{K}$ (Fig. 2) with exponents $\delta = 1.20(1)$ and $\beta = 0.39(1)$, fairly typical of a three-dimensional Heisenberg system. At 62 K there is a subtle change in behavior of v_1 involving a discontinuous change in the gradient of the measured frequency [Fig. 2(a)] corresponding to the transition at $T_{\rm N2}$. It is worth noting that our measured values of the temperatures of the two magnetic phase transitions differ slightly from results reported in Ref. [7] based on bulk magnetic susceptibility measurements. This is possibly due to slight variation between samples, but differences in the sharpness of the transitions between the two experimental techniques makes precise comparisons of transition temperatures difficult. The transition at T_{N1} is very sharp in the μ^+SR data but broad in the susceptibility, and the lower transition at T_{N2} is discontinuous in the susceptibility but quite subtle in our μ^+ SR results.

We carried out supporting muon-site computations using the MuFinder software [30]. We populated a supercell of the structure made up of $2 \times 2 \times 2$ conventional unit cells with muons at random positions with the constraint of a minimum distance between each initial muon position of 1 Å and a minimum muon-atom distance of 1 Å. Geometry optimiza-

tions were then performed using the CASTEP [31] code to relax the geometry of the full structure, causing muons to fall into local minima of energy. Calculations were carried out using the PBE functional [32], with a plane wave basis set cut-off energy of 465 eV and a k-point grid of size $2 \times 2 \times 1$. Following a geometry optimization, muons were grouped into symmetry-equivalent positions so that they could be clustered into similar stopping sites. Our measurements of both the monoclinic ($T < T_{N2}$) and trigonal ($T_{N2} < T < T_{N1}$) structures are consistent with a single low-energy stopping site. The minimum energy sites for both structural phases are found to share the same local environment, between the Ni²⁺ ion and the nearest I^- ion, as pictured in Fig. 1(b). Using this candidate stopping site we can calculate the local dipole field experienced by implanted muons and then construct simulated μ^+ SR spectra for comparison with the data. The simulated polarization is computed using

$$P_{z}(t) = \sum_{i} f_{z,i}^{2} p_{i} + \sum_{i} \left(1 - f_{z,i}^{2} \right) p_{i} \cos(\gamma_{\mu} B_{i} t), \quad (3)$$

where the probabilities p_i correspond to the distribution of magnetic field strengths felt by muons stopping in the sample, B_i is the magnitude of the local field, and $f_{z,i} = B_{z,i}/B_i$ is the computed ratio of the *z* component of magnetic field to the overall local field magnitude.

The low-temperature magnetic ground state is predicted to be helimagnetic, with a spin spiral which has a component along the *a* axis that results in one complete rotation of the spin across roughly seven unit cells [7,22], described by the spin propagation vector $\mathbf{q} = (0.138, 0, 0.1457)$. Computing the resulting local dipole field with an ordered Ni ion moment of $1.6\mu_{\rm B}$ [6] at the predicted low-energy muon site yields a distribution of fields felt by muons in structurally equivalent but magnetically inequivalent sites [Fig. 1(c)]. This distribution shows two prominent peaks, and a simulated spectrum is therefore dominated by oscillations at two frequencies with associated fields corresponding to the peaks. However, our muon site calculations indicate that there is a very shallow local minimum in energy about the candidate site, and a large number of sites with small displacements (all within 0.4 Å of each other) from the average are found in the calculations. Each displacement will result in a field distribution similar to that shown in Fig. 1(c), but with the two peaks at different values of local field. Taking the normalized sum of the dipole field contributions from each of these sites therefore broadens the two peaks such that they overlap, resembling a single gaussian peak centered on an average field of 0.867 T, equivalent to a precession frequency of 117 MHz. This frequency is in excellent agreement with our single measured frequency of 117(5) MHz close to T = 0 K. Finally, calculating a simulated zero temperature spectrum from this overall probability distribution and applying the same fitting function used for the data gives a crude estimate for the relaxation of $\lambda_1 = 175 \,\mu s^{-1}$. Compared to our experimental value of $\lambda_1 = 120(18) \,\mu s^{-1}$, this suggests that the relaxation in the oscillating component is largely accounted for by decoherence due to this distribution of local fields, with relatively little dynamic contribution. Spin-DFT calculations in other work on this material suggests that the magnetic ground state is complicated by a magnetization of the I ions by the Ni ions [22]. We found, however,



FIG. 3. Temperature evolution of parameters from fits to Eq. (4) for ZF data. (a) Initial asymmetry, $A_0 = A(t = 0)$ (inset: A_0 in the region T < 85 K [left axis, black] and fitted baseline, A_8 , of the measurements in TF [right axis, red]) and (b) relaxation rate λ_4 with power law fits in different regions.

that we were able to produce simulated spectra that agreed well with the experiment, assuming magnetic centers on the Ni ions only.

In the intermediate temperature regime $T_{N2} < T < T_{N1}$, the magnetic structure is predicted to be a simple antiferromagnet with the spin propagation vector (0, 0, 1/2). A similar dipole field analysis in this case gives an average field of B = 0.695 T, corresponding to a T = 0 K precession frequency of v = 93 MHz for this structure. An extrapolation of the fitted frequency data in this region with the order parameter fit described above suggests a T = 0 K frequency of v = 92(5) MHz, in good agreement with this theoretical value, though it should be noted that this fit is not strongly constrained owing to the small number of data points in this region.

We carried out further measurements on a polycrystalline sample using the HiFi instrument (at the STFC-ISIS Facility) [33], which allows for observation of the longer-time behavior in order to probe dynamics. ZF measurements were made across the same temperature interval as for the single-crystal measurements. In this case the oscillations are not resolvable as they occur over too short a period compared to the ISIS pulse width. Asymmetry spectra were therefore fitted to the function

$$A(t) = A_4 e^{-\lambda_4 t} + A_5, \tag{4}$$

with a nonvarying background term A_5 held constant at 13.6% (largely accounted for by muons stopping in the silver outside the sample), from which an initial asymmetry $A_0[=A(t=0)]$ can be calculated for each temperature via $A_0 = A_4 + A_5$. Results of the fitting procedure are shown in Fig. 3. We see indications of phase transitions at both T_{N1} and T_{N2} , with A_0 decreasing from around 30 K, then undergoing a more rapid drop around $T_{N2} \approx 58$ K followed by a sharp increase at $T_{N1} \approx 73$ K.

We would expect the high temperature data $(T > T_{N1})$ to include the full relaxing asymmetry A_{rel} resulting from all muons implanted in the sample, excluding background contributions. In a fully ordered magnetic state in a powder we expect to see only 1/3 of the relaxing asymmetry resulting from muon spins initially parallel to the local field. The remaining 2/3, corresponding to spin-components initially perpendicular to the local field, result in oscillations outside of the ISIS frequency response window, that are not observed. Notably, in the intermediate region $T_{N2} < T < T_{N1}$, an additional 1.4% of asymmetry is lost, which implies that new relaxation channels are accessed in this regime that were not active below T_{N2} .

The dynamic signature of the magnetism is accessible via the longitudinal relaxation rate λ_4 , which rises approximately linearly with increasing temperature up to a broad peak, which occurs ≈ 10 K below T_{N2} . The rate λ_4 then falls to a constant value in the region between transitions, before increasing to a second peak at 73 K. Such dynamics peaks are often indicative of local field fluctuation rates that decrease close to magnetic transitions. Below T_{N2} , the evolution of $\lambda_4(T)$ is consistent with the fluctuations from spin-wave excitations in the case of a single gapless magnon band [34–36], for which we expect $\lambda \propto T^p$. We obtain a good fit to the data below 50 K with p = 1, where

$$p = \frac{2D}{s} - 1. \tag{5}$$

Here *D* is the effective dimensionality (which we expect to be 1 here since the magnetic structure is described by a single propagation vector) and s = 1 is the exponent for the spin wave dispersion relation $\omega = q^s$. Our exponent p = 1 is consistent with s = D = 1, corresponding to the helimagnetic magnetic structure predicted. This implies that the dynamics in this range are well described by contributions from a single magnon band that dominates the magnetic excitations.

In the intermediate temperature region $T_{N2} < T < T_{N1}$, we again expect s = 1, owing to the simple antiferromagnetic spin texture. However, here the T independence of the relaxation rate data suggests p = 0, which cannot be satisfied for integer D. This suggests that above 60 K the dynamics we detect through the relaxation rate λ_4 are qualitatively different from those for $T < T_{N2}$, and can no longer be described by a single gapless magnon band. Moreover, temperature dependent fluctuations suggest that the relaxation in this regime is no longer affected by the population of collective magnon excitations, nor dominated by the excitation of the system over an energy gap (e.g., that resulting from single-ion anisotropy arising from the spin-orbit interaction). It is also possible that paraelectric fluctuations in this region complicate the observed dynamics, but the nature of the dynamics in this range are not made clear by our muon spectroscopy measurements.

It seems that the new magnetic structure stabilized when the crystal distorts above T_{N2} is such that the main relaxation channel for the muons ceases to be the result of magnons, although it is by no means obvious which excitations are dominant in this regime. We suggest, however, that the changes in relaxation are ultimately driven by the distortion of the crystal. Specifically, below T_{N2} the local environment around the Ni²⁺ ions changes symmetry as the unit cell goes from trigonal to monoclinic with decreasing temperature. Above T_{N2} the structure has the point group D_{3d} at the Ni²⁺ ion center and the partially filled eight-electron 3d shell of the Ni²⁺ ion is split into three groups, with the $d_{x^2-v^2}$ and d_{xy} , and the d_{xz} and d_{vz} orbitals forming two distinct degenerate bands separated in energy, and the d_{7^2} orbital occupying a different energy still. An observation of the shapes of the superpositions of these orbitals suggests that d_{r^2} is likely to be the lowest energy state as it allows for electrons to be localized further away from the I⁻ anions. This energy level structure will result in a partial filling of whichever is the higher energy out of the $d_{x^2-y^2} + d_{xy}$ and $d_{xz} + d_{yz}$ bands. Below T_{N2} the structure becomes much less symmetric, losing centrosymmetry and allowing for the presence of the Dzyaloshinskii-Moriya (DM) interaction which results in the spin-canted noncollinear magnetic ground state in this phase. This lowering of symmetry also results in the loss of any rotation axis, meaning the structure must now take on one of three low-symmetry point groups at the Ni²⁺ ion center, all of which would lift each of the orbital degeneracies, creating energy gaps between different electronic states in the 3d orbitals. It seems reasonable to suggest that this change in orbital arrangement, which might be expected to drive a change in superexchange couplings, and the possibility of a sizable DM interaction leads to the altered magnetic structure with a qualitatively different spectrum of excitations.

In addition to our ZF measurements, we made measurements in a weak applied transverse field (TF) for both single crystal (5 mT) and powder samples (2 mT). Weak TF measurements allow us to determine the nonmagnetic fraction of the material as the muon spins in such regions precess in the small applied field, resulting in an oscillating component in the asymmetry with amplitude proportional to the nonmagnetic volume measured. Muons stopping in ordered regions where the static field is much larger will not contribute to this oscillatory component. We found that spectra for single crystals and powder were qualitatively similar and that parameters from fits to the two data sets behaved in the same way. After fitting the α parameter discussed in Sec. II from measurements made at temperatures above 70 K, we fit the data to an equation of the form

$$A(t) = A_6 e^{-\lambda_6 t} \cos(2\pi v_6 t) + A_7 e^{-\lambda_7 t} + A_8.$$
(6)

Here the first term corresponds to precession of the muon spins in the nonmagnetic regions (which will include regions outside the sample) with a fixed frequency corresponding to the strength of the weak applied field, the second term is a relaxing exponential term, found to have a larger relaxation than that seen in ZF, and the third term is a constant baseline asymmetry that we allowed to vary in our fitting. We found that the amplitude A_6 remains constant up to 70 K, before increasing upon entering the paramagnetic region as expected. This implies that there is no change in the nonmagnetic fraction between the two low-*T* ordered phases in the material, and therefore no macroscopic phase separation occurring in the material within the ordered regimes.

The fitted baseline asymmetry, A_8 , for the powder data is plotted in the inset in Fig. 3. We observe a nonzero baseline asymmetry at low temperatures, which decreases on warming from 30 K to 50 K, above which it remains approximately zero. A nonzero value of this term indicates the presence of

muon spins that are not relaxed within the time window of the measurement. We would expect this in a conventional quasistatic magnetically ordered phase, where some muon spins will initially be parallel to the local field and will therefore be locked in direction during the measurement and not contribute to the relaxation. The decrease in this baseline on warming coincides with our observation of a decrease in A_0 above 30 K in ZF, seen even before the system enters the region of unconventional dynamics at temperatures $T_{N2} < T < T_{N1}$ on warming. This suggests that at temperatures below T_{N2} , dynamic relaxation channels are causing muon-spin flips, resulting in muon spins being relatively rapidly relaxed on the timescale of the ISIS frequency response. The baseline contribution vanishes at those temperatures above which the ZF relaxation rate λ_4 ceases to follow a linear temperature dependence. This is consistent with the new relaxation channels being activated as the system is warmed toward the region of more complicated dynamics that characterizes the phase at $T_{N2} < T < T_{N1}$.

The additional exponential term with amplitude A_7 was unexpected, but indicates the presence of an additional contribution to the relaxation, possibly from magnetic defects. This term is present in both the powder and the single crystal measurements, and in both cases the amplitude A_7 and the relaxation rate λ_7 are constant on warming up to 50 K, and increase through the intermediate phase $T_{N2} < T < T_{N1}$. The term persists at temperatures just above the transition into magnetic disorder. We are not able to unambiguously discern what causes this term, but it may be explained by the presence of magnetic defects such as spins being frozen around stacking faults. These kinds of defects are likely to appear in layered materials such as NiI₂, and could be exacerbated in this case by the structural transition at T_{N2} , about which there may be coexisting regions of both structural phases.

IV. CONCLUSIONS

In conclusion, muon-spin spectroscopy measurements have shown features corresponding to two successive phase transitions at $T_{\rm N1} \approx 73$ K and $T_{\rm N2} \approx 60$ K. With the addition of a DFT muon stopping site analysis, we have been able to identify a muon site located between neighboring Ni and I ions, at which the muon spin behavior is consistent with the proposed magnetic structure, assuming we allow a small variation in the location where the site is realized. The dynamic relaxation shows a linear increase in the region below 58 K, followed by a constant region between transitions, indicative of a qualitative change in excitation spectrum, which coincides with the change in magnetic structure. It is worth noting that the prediction of skyrmions in a monolayer of this material was for a phase occurring at temperatures close to the ordering temperature, where skyrmions were presumably stabilized by thermal fluctuations. Given that we have identified two regimes of dynamics, it will be interesting in the future to see whether either region is able to support the equilibrium occurrence of skyrmion excitations in applied magnetic field in samples formed from a limited number of layers.

ACKNOWLEDGMENTS

This work is partially based on experiments performed at the Swiss Muon Source $S\mu S$, Paul Scherrer Institute, Villigen,

Switzerland, and at the STFC-ISIS Facility, UK; we are grateful for the provision of beamtime. We also thank Chennan Wang and Hubertus Luetkens (S μ S) for their assistance over the course of these measurements. Computational work was carried out using the Hamilton8 HPC service of Durham University and the ARCHER2 UK National Supercomputing Service [37]. We acknowledge support from EPSRC (UK)

- K. S. Burch, D. Mandrus, and J. Park, Magnetism in twodimensional van der Waals materials, Nature (London) 563, 47 (2018).
- [2] Q. H. Wang, A. Bedoya-Pinto, M. Blei, A. H. Dismukes, A. Hamo, S. Jenkins, M. Koperski, Y. Liu, Q. Sun, E. J. Telford *et al.*, The magnetic genome of two-dimensional van der Waals materials, ACS Nano 16, 6960 (2022).
- [3] T. Lancaster, Skyrmions in magnetic materials, Contemp. Phys. 60, 246 (2019).
- [4] S. Kezilebieke, M. N. Huda, V. Vaňo, M. Aapro, Somesh C. Ganguli, O. J. Silveira, S. Głodzik, A. S. Foster, T. Ojanen, and P. Liljeroth, Topological superconductivity in a van der Waals heterostructure, Nature (London) 588, 424 (2020).
- [5] G. Zhang, H. Wu, L. Zhang, L. Yang, Y. Xie, F. Guo, H. Li, B. Tao, G. Wang, W. Zhang *et al.*, Two-Dimensional Van Der Waals Topological Materials: Preparation, Properties, and Device Applications, Small 18, 2204380 (2022).
- [6] M. A. McGuire, Crystal and magnetic structures in layered, transition metal dihalides and trihalides, Crystals 7, 121 (2017).
- [7] T. Kurumaji, S. Seki, S. Ishiwata, H. Murakawa, Y. Kaneko, and Y. Tokura, Magnetoelectric responses induced by domain rearrangement and spin structural change in triangular-lattice helimagnets NiI₂ and CoI₂, Phys. Rev. B 87, 014429 (2013).
- [8] D. Amoroso, P. Barone, and S. Picozzi, Spontaneous skyrmionic lattice from anisotropic symmetric exchange in a Ni-halide monolayer, Nat. Commun. 11, 5784 (2020).
- [9] M. Blei, J. L. Lado, Q. Song, D. Dey, O. Erten, V. Pardo, R. Comin, S. Tongay, and A. S. Botana, Synthesis, engineering, and theory of 2D van der Waals magnets, Appl. Phys. Rev. 8, 021301 (2021).
- [10] Q. Song, C. A. Occhialini, E. Ergeçen, B. Ilyas, D. Amoroso, P. Barone, J. Kapeghian, K. Watanabe, T. Taniguchi, A. S. Botana *et al.*, Evidence for a single-layer van der Waals multiferroic, Nature (London) **602**, 601 (2022).
- [11] T. Lancaster, F. Xiao, Z. Salman, I. O. Thomas, S. J. Blundell, F. L. Pratt, S. J. Clark, T. Prokscha, A. Suter, S. L. Zhang *et al.*, Transverse field muon-spin rotation measurement of the topological anomaly in a thin film of MnSi, Phys. Rev. B 93, 140412(R) (2016).
- [12] A. Amato, P. Dalmas de Réotier, D. Andreica, A. Yaouanc, A. Suter, G. Lapertot, I. M. Pop, E. Morenzoni, P. Bonfà, F. Bernardini *et al.*, Understanding the μSR spectra of MnSi without magnetic polarons, Phys. Rev. B **89**, 184425 (2014).
- [13] T. J. Hicken, S. J. R. Holt, K. J. A. Franke, Z. Hawkhead, A. Štefančič, M. N. Wilson, M. Gomilšek, B. M. Huddart, S. J. Clark, M. R. Lees *et al.*, Magnetism and Néel skyrmion dynamics in GaV₄S_{8-y}Se_y, Phys. Rev. Res. 2, 032001(R) (2020).

(Grants No. EP/N032128/1, No. EP/X035891/1, and No. EP/T005963/1 and T.L.B's studentship). N.P.B is grateful for the support of the Durham Doctoral Scholarship.

DATA AVAILABILITY

Data will be made available via [38].

- [14] T. J. Hicken, M. N. Wilson, K. J. A. Franke, B. M. Huddart, Z. Hawkhead, M. Gomilšek, S. J. Clark, F. L. Pratt, A. Štefančič, A. E. Hall *et al.*, Megahertz dynamics in skyrmion systems probed with muon-spin relaxation, Phys. Rev. B **103**, 024428 (2021).
- [15] T. J. Hicken, Z. Hawkhead, M. N. Wilson, B. M. Huddart, A. E. Hall, G. Balakrishnan, C. Wang, F. L. Pratt, S. J. Clark, and T. Lancaster, Energy-gap driven low-temperature magnetic and transport properties in $Cr_{1/3}MS_2$ (M = Nb, Ta), Phys. Rev. B **105**, L060407 (2022).
- [16] P. Day, A. Dinsdale, E. R. Krausz, and D. J. Robbins, Optical and neutron diffraction study of the magnetic phase diagram of NiBr₂, J. Phys. C 9, 2481 (1976).
- [17] P. Day and K. R. A. Ziebeck, Incommensurate spin structure in the low-temperature magnetic phase of NiBr₂, J. Phys. C 13, L523 (1980).
- [18] D. Billerey, C. Terrier, N. Ciret, and J. Kleinclauss, Neutron diffraction study and specific heat of antiferromagnetic NiI₂, Phys. Lett. A **61**, 138 (1977).
- [19] J. Kapeghian, D. Amoroso, C. A. Occhialini, L. G. P. Martins, Q. Song, J. S. Smith, J. J. Sanchez, J. Kong, R. Comin, P. Barone *et al.*, Effects of pressure on the electronic and magnetic properties of bulk NiI₂, Phys. Rev. B **109**, 014403 (2024).
- [20] H. Liu, X. Wang, J. Wu, Y. Chen, J. Wan, R. Wen, J. Yang, Y. Liu, Z. Song, and L. Xie, Vapor deposition of magnetic van der Waals NiI₂ crystals, ACS Nano 14, 10544 (2020).
- [21] S. R. Kuindersma, J. P. Sanchez, and C. Haas, Magnetic and structural investigations on NiI₂ and CoI₂, Physica B+C 111, 231 (1981).
- [22] A. O. Fumega and J. L. Lado, Microscopic origin of multiferroic order in monolayer NiI₂, 2D Mater. 9, 025010 (2022).
- [23] H. Ju, Y. Lee, K. Kim, I. H. Choi, C. J. Roh, S. Son, P. Park, J. H. Kim, T. S. Jung, J. H. Kim *et al.*, Possible persistence of multiferroic order down to bilayer limit of van der Waals material NiI₂, Nano Lett. **21**, 5126 (2021).
- [24] D. Lebedev, J. T. Gish, E. S. Garvey, T. K. Stanev, J. Choi, L. Georgopoulos, T. W. Song, H. Y Park, K. Watanabe, T. Taniguchi *et al.*, Electrical Interrogation of Thickness-Dependent Multiferroic Phase Transitions in the 2D Antiferromagnetic Semiconductor NiI₂, Adv. Funct. Mater. **33**, 2212568 (2023).
- [25] M. Yoshinaga, T. Iida, M. Noda, T. Endo, and Y. Takanashi, Bulk crystal growth of Mg₂Si by the vertical Bridgman method, Thin Solid Films 461, 86 (2004).
- [26] S. Blundell, R. De Renzi, T. Lancaster, and F. L. Pratt, *Muon Spectroscopy: An Introduction* (Oxford University Press, Oxford, 2022).

- [27] F. L. Pratt, WIMDA: a muon data analysis program for the Windows PC, Phys. B: Condens. Matter 289-290, 710 (2000).
- [28] A. Amato, H. Luetkens, K. Sedlak, A. Stoykov, R. Scheuermann, M. Elender, A. Raselli, and D. Graf, The new versatile general purpose surface-muon instrument (GPS) based on silicon photomultipliers for μ SR measurements on a continuous-wave beam, Rev. Sci. Instrum. **88**, 093301 (2017).
- [29] See Supplemental Material at http://link.aps.org/supplemental/ 10.1103/PhysRevB.111.104420 for details of our fitting of the weak transverse field data measured at ISIS, along with example raw asymmetry spectra showing a change in the amplitude A₁ of the oscillating component in zero field data measured at PSI.
- [30] B. M. Huddart, A. Hernández-Melián, T. J. Hicken, M. Gomilšek, Z. Hawkhead, S. J. Clark, F. L. Pratt, and T. Lancaster, MuFinder: A program to determine and analyse muon stopping sites, Comput. Phys. Commun. 280, 108488 (2022).
- [31] S. J. Clark, M. D. Segall, C. J. Pickard, P. J. Hasnip, M. I. J. Probert, K. Refson, and M. C. Payne, First principles meth-

ods using CASTEP, Z. Kristallogr.-Cryst. Mater. 220, 567 (2005).

- [32] J. P. Perdew, K. Burke, and M. Ernzerhof, Generalized gradient approximation made simple, Phys. Rev. Lett. 77, 3865 (1996).
- [33] P. J. C. King, R. de Renzi, S. P. Cottrell, A. D. Hillier, and S. F. J. Cox, ISIS muons for materials and molecular science studies, Phys. Scr. 88, 068502 (2013).
- [34] M. Gomilšek, T. J. Hicken, M. N. Wilson, K. J. A. Franke, B. M. Huddart, A. Štefančič, S. J. R. Holt, G. Balakrishnan, D. A. Mayoh, M. T. Birch, S. H. Moody, H. Luetkens, Z. Guguchia, M. T. F. Telling, P. J. Baker, S. J. Clark, and T. Lancaster, Skyrmion and incommensurate spin dynamics in centrosymmetric Gd₂PdSi₃, Phys. Rev. Lett. **134**, 046702 (2025).
- [35] D. Beeman and P. Pincus, Nuclear spin-lattice relaxation in magnetic insulators, Phys. Rev. 166, 359 (1968).
- [36] N. Janša, A. Zorko, M. Gomilšek, M. Pregelj, K. W. Krämer, D. Biner, A. Biffin, C. Rüegg, and M. Klanjšek, Observation of two types of fractional excitation in the Kitaev honeycomb magnet, Nat. Phys. 14, 786 (2018).
- [37] https://www.archer2.ac.uk.
- [38] DOI:10.15128/r1pn89d6605.